

# AltroFoam RF 150

Preliminary Data Sheet  
Density 150 kg/m<sup>3</sup>

# altropol

## Main features

- without fluorinated hydrocarbons as blowing agents
- processible by hand and machine
- usable in unheated moulds
- low density

## Applications

- component parts for industrial applications
- backfillings

## Properties in the non-crosslinked state 20 °C (approx. values)

		AltroFoam RF 150 Comp. A	AltroFoam RF 150 Comp. B
Colour		transparent	brown
Mixing ratio	p.b.w.	100	115
Mixing ratio	p.b.v.	95	93
Density	g/cm <sup>3</sup>	1.05	1.24
Viscosity	mPa·s	800	200

## Properties of the mixture at 20 °C (approx. values)

Mixed viscosity (25 °C)	mPa·s	500
Start time	seconds	35
Setting/ thread tension time	minutes	not determined
Rise time	minutes	2
Tack-free	minutes	5
Density (free-rise foamed)	kg/m <sup>3</sup>	150
Expansion behaviour	fach	6.5

## How to process the material

Stir up AltroFoam RF 150 Comp. A intensively prior to processing.

In case of manual processing, pour at first component A into the mixing vessel. After having added component B, mix the compound thoroughly and proceed to casting immediately.

The most suitable device for mixing is a high-speed stirrer with approx. 1000 rpm.

Material and processing temperature should be at least 20 °C.

The products are highly sensitive to humidity.

Close receptacles tightly after every use.

Heat up moulds for rigid integral parts to 45 - 50 °C prior to injection.

For free-rise foamed applications, preheating is not necessary.

**AltroFoam RF 150**  
Preliminary Data Sheet  
Density 150 kg/m<sup>3</sup>

**altropol**

**Form of delivery**

AltroFoam RF 150 Comp. A	0.87 kg	8.7 kg	200 kg
AltroFoam RF 150 Comp. B	1 kg	10 kg	250 kg

**Storage**

We recommend keeping the material in tightly closed original receptacles at temperatures of 20 - 25 °C. When duly stored, the material can be used within the shelf life indicated on the labels (the first 2 digits of the batch number indicate the week, the 3rd digit indicates the year).

**Measure of precaution**

With the aid of the current safety data sheets, which contain physical, ecological, toxicological and other data relating to safety, the user can inform himself on the safe handling and storage of the products.

---

Our technical service - in words, in writing or by trials - is given according to the current state of our knowledge. It does however not relieve the customer / user from the duty to check by himself if the products supplied by us are suitable for the intended processes and purposes. Application, use and processing of the products take place beyond our control possibilities and lie therefore exclusively in the area of responsibility of the processor. Any existing property rights of third parties are to be considered. We guarantee the perfect quality of our products in accordance with our general terms and conditions of business. When handling our products you have to observe the legal rules and the rules for the industrial hygiene. As for the rest, we refer to the corresponding safety data sheets.

• 2023-09-27.2 / 12 / LW-W •

---

• [www.altropol.de](http://www.altropol.de) •

• Altropol Kunststoff GmbH • Rudolf-Diesel-Straße 9 - 13 • D-23617 Stockelsdorf • Tel. +49 (0)451-499 60-0 •  
• Fax. +49 (0)451-499 60-20 • E - Mail: [info@altropol.de](mailto:info@altropol.de) •