

AltroFoam RF 200

Preliminary Data Sheet
Density 200 kg/m³

altropol

Main features

- without fluorinated hydrocarbons as blowing agents
- processible by hand and machine
- usable in unheated moulds
- low density

Applications

- component parts for industrial applications
- backfillings

Properties in the non-crosslinked state 20 °C (approx. values)

		AltroFoam RF 200 Comp. A	AltroFoamRF 200 Comp. B
Colour		transparent	brown
Mixing ratio	p.b.w.	100	110
Mixing ratio	p.b.v.	95	89
Density	g/cm ³	1.05	1.24
Viscosity	mPa·s	750	200

Properties of the mixture at 20 °C (approx. values)

Mixed viscosity (25 °C)	mPa·s	450
Start time	seconds	35
Setting/thread tension time	minutes	not determined
Rise time	minutes	*
Tack-free	minutes	*
Density (free-rise foamed)	kg/m ³	200
Expansion behaviour	fold	5

* work in progress

How to process the material

Stir up AltroFoam RF 200 Comp. A intensively prior to processing.

In case of manual processing, pour at first component A into the mixing vessel. After having added component B, mix the compound thoroughly and proceed to casting immediately.

The most suitable device for mixing is a high-speed stirrer with approx. 1000 rpm.

Material and processing temperature should be at least 20 °C.

The products are highly sensitive to humidity.

Close receptacles tightly after every use.

Heat up moulds for rigid integral parts to 45 - 50 °C prior to injection.

For free-rise foamed applications, preheating is not necessary.

AltroFoam RF 200
Preliminary Data Sheet
Density 200 kg/m³

altropol

Lieferform

AltroFoam RF 200 Comp. A	0.9 kg	9 kg	200 kg
AltroFoam RF 200 Comp. B	1 kg	10 kg	250 kg

Storage

We recommend keeping the material in tightly closed original receptacles at temperatures of 20 - 25 °C. When duly stored, the material can be used within the shelf life indicated on the labels (the first 2 digits of the batch number indicate the week, the 3rd digit indicates the year).

Measure of precaution

With the aid of the current safety data sheets, which contain physical, ecological, toxicological and other data relating to safety, the user can inform himself on the safe handling and storage of the products.

Our technical service - in words, in writing or by trials - is given according to the current state of our knowledge. It does however not relieve the customer / user from the duty to check by himself if the products supplied by us are suitable for the intended processes and purposes. Application, use and processing of the products take place beyond our control possibilities and lie therefore exclusively in the area of responsibility of the processor. Any existing property rights of third parties are to be considered. We guarantee the perfect quality of our products in accordance with our general terms and conditions of business. When handling our products you have to observe the legal rules and the rules for the industrial hygiene. As for the rest, we refer to the corresponding safety data sheets.

• 2023-09-26.3 / 12 / LW-W •

• www.altropol.de •

• Altropol Kunststoff GmbH • Rudolf-Diesel-Straße 9 - 13 • D-23617 Stockelsdorf • Tel. +49 (0)451-499 60-0 •
• Fax. +49 (0)451-499 60-20 • E - Mail: info@altropol.de •