

**Main features**

- high resistance to initial tearing and tear propagation
- very good flow properties

**Applications**

- mould making

**Properties in the non-crosslinked state (approx. values)**

		<b>NEUKASIL SN 1995</b>	<b>NEUKASIL Crosslinker C 1</b>
Colour		red brown	colourless
Mixing ratio	p.b.w.	100	5
Density (20 °C)	g/cm <sup>3</sup>	1.268	0.90
Viscosity (20° C)	mPa·s	15,000	30

**Properties of the mixture and the cured product (approx. values)**

Mixed viscosity	mPa·s		9,000
Pot life (RT 1000g)	minutes		120
tack-free depending on layer thickness	hours		24
Hardness Shore A (24h)	points	DIN 53505	45
Hardness Shore A (7d)	points	DIN 53505	55
Tensile strength	N/mm <sup>2</sup>	DIN 53504	3.5
Elongation at break	%	DIN 53504	130
Resistance to tear propagation	N/mm	ASTM D 624 B	2.8
Linear dimensional change	%		1

(RT = room temperature)

**How to process the material**

For the preparation of a formulation being ready for processing, add the required quantity of crosslinker to the rubber and stir the compound until it is homogeneous. See that as little air as possible gets into the compound while stirring. To obtain a bubble-free vulcanized material, we recommend evacuating the crosslinker-containing formulation before continuing the processing.

When the vacuum is created, the mixture increases in volume by 3 to 4 times of its original volume under formation of bubbles. The degassing process is finished when the bubbles have collapsed and the formulation has reobtained its original volume. Avoid a longer stay of the crosslinker-containing formulation in the vacuum as otherwise you run the risk that parts of the crosslinkers will be removed. Carefully cast the prepared material without enclosing bigger quantities of air again.

When NEUKASIL SN 1995 is used as mould making material (production of negatives), there is no release agent required for demoulding. Should there still arise any problems, we recommend our NEUKADUR Release Agent SE New or NEUKADUR Release Spray P 6. For the production of multipart moulds and to avoid an adhesion of NEUKASIL SN 1995 to itself, use the same release agents. Treat the surface of the part already vulcanized with release agent, then cast the second part of the mould.

For release agents, please visit our homepage under <http://www.altropol.de/en/produkte/weitere-produkte/trennmittel>

**NEUKASIL SN 1995**  
Silicone Rubber  
condensation-crosslinking

**altropol**

**Form of delivery**

NEUKASIL SN 1995	1 kg	5 kg	25 kg
NEUKASIL Crosslinker C 1	0.05 kg	0.25 kg	1.25 kg

**Storage**

We recommend keeping the material in tightly closed original receptacles at temperatures of 20 - 25 °C. When duly stored, the material can be used within the shelf life indicated on the labels (the first 2 digits of the batch number indicate the week, the 3rd digit indicates the year).

**Measure of precaution**

With the aid of the current safety data sheets, which contain physical, ecological, toxicological and other data relating to safety, the user can inform himself on the safe handling and storage of the products.

---

Our technical service - in words, in writing or by trials - is given according to the current state of our knowledge. It does however not relieve the customer / user from the duty to check by himself if the products supplied by us are suitable for the intended processes and purposes. Application, use and processing of the products take place beyond our control possibilities and lie therefore exclusively in the area of responsibility of the processor. Any existing property rights of third parties are to be considered. We guarantee the perfect quality of our products in accordance with our general terms and conditions of business. When handling our products you have to observe the legal rules and the rules for the industrial hygiene. As for the rest, we refer to the corresponding safety data sheets.

• 2024-02-16.1 / 12 / LW-W •

---

• [www.altropol.de](http://www.altropol.de) •

• Altropol Kunststoff GmbH • Rudolf-Diesel-Straße 9 - 13 • D-23617 Stockelsdorf • Tel. +49 451-499 60-0 •  
• Fax. +49 451-499 60-20 • E - Mail: [info@altropol.de](mailto:info@altropol.de) •