

Main features

- properties similar to those of ABS
- low-viscous
- high dimensional stability under heat
- very impact-resistant

Applications

- production of parts
- prototyping
- universally for all kinds of moulds and patterns

Properties in the non-crosslinked state (approx. values)

		NEUKADUR ProtoCast 115	NEUKADUR Hardener PTG 1	NEUKADUR Hardener PTG 4
Colour		milky white	yellowish	brownish
Mixing ratio	p.b.w.	100	120	100
Density 20 °C	g/cm ³	1.00	1.20	1.20
Viscosity 25 °C	mPa·s	1,200	100	150

Properties of the mixture (approx. values)

			NEUKADUR ProtoCast 115 Hardener PTG 1	NEUKADUR ProtoCast 115 Hardener PTG 4
Mixed viscosity (25 °C)	mPa·s		600	800
Pot life 25 °C	minutes		4	4
Demouldable after (8 °C)	minutes		45	45
Hardness	Shore D	DIN 53505	83	83
Colour			light beige	beige
Recommended layer thickness	mm		5	5

Mechanical values (approx. values after 90 min 90 °C)

Tensile strength	MPa	DIN 53455	60	60
Tensile elongation	%	DIN 53455	15	13
Flexural strength	MPa	DIN 53452	100	105
Bending elongation	%	DIN 53452	10	8.5
Modulus in flexure	MPa	DIN 53457	1,750	1,750
Dimensional stability under heat	°C	HDT	105	105
Impact strength	KJ/m ²	DIN 51230	30	30
Linear dimensional change	%	500 x 50 x 3 mm	0.1	0.1

How to process the material

Prior to use, stir up NEUKADUR ProtoCast 115 thoroughly.

Mix both components intensively at room temperature according to the indicated mixing ratio.

Before casting make sure that parts and moulds are free from humidity and non-evaporated release agent.

For release agents, please visit our home page under <http://www.altropol.de/en/produkte/weitere-produkte/trennmittel/>

NEUKADUR ProtoCast 115

2-C PUR Vacuum Casting System

ABS

altropol

By the use of NEUKADUR Hardener PTG 1, the elasticity will be increased.

A better dimensional stability under heat and a higher modulus of elasticity are achieved by the use of NEUKADUR Hardener PTG 4.

Form of delivery

NEUKADUR ProtoCast 115	1 kg	5 kg
NEUKADUR Härter PTG 1	1 kg	5 kg
NEUKADUR Härter PTG 4	1 kg	5 kg

Storage

The material should be kept in tightly closed original receptacles at temperatures of 20 – 25 °C. When duly stored, the material can be used within the shelf life indicated on the labels (the first 2 digits of the batch number indicate the week, the 3rd digit indicates the year).

Measure of precaution

Users should make use of the current safety data sheets, which contain physical, ecological, toxicological, and other data relating to safety, to inform themselves on the safe handling and storage of products.

Our technical service - in words, in writing or by trials - is given according to the current state of our knowledge. It does however not relieve the customer/user from the duty to check by himself if the products supplied by us are suitable for the intended processes and purposes. Application, use and processing of the products take place beyond our control possibilities and lie therefore exclusively in the area of responsibility of the processor. Any existing property rights of third parties are to be considered. We guarantee the perfect quality of our products in accordance with our general terms and conditions of business. When handling our products you have to observe the legal rules and the rules for the industrial hygiene. As for the rest, we refer to the corresponding safety data sheets.

• 2017-08-21.3 / 4 / LW-W •

• www.altropol.de •

• Altropol Kunststoff GmbH • Rudolf-Diesel-Straße 9 - 13 • D-23617 Stockelsdorf • Tel. +49 (0)451-499 60-0 •
• Fax. +49 (0)451-499 60-20 • E - Mail: info@altropol.de •