

NEUKAPOL 9028
Branched Polyester/-ether
Universal binder

altropol

Main features

- hydrophobic
- low-viscous
- 100 % solid content
- solventfree

Applications

- 2-C PUR Coatings
- corrosion protection
- adhesives
- casting compounds

Product properties (approx. values)

			NEUKAPOL 9028
Colour			yellow
OH-value	mg KOH / g	DIN 53240	218 ± 15
Viscosity 25°C	mPa·s	Brookfield RVT	750 ± 250
Water content	%		< 0.2
Acid number	mg KOH / g	DIN EN ISO 2114	< 3

Properties of the mixture [94.50 p.b.w. NEUKAPOL 9028 + 5 p.b.w. NEUKADUR Zeolith L Paste + 0.5 p.b.w. Defoamer NEUKAPOL PN 9079 + 55.28 p.b.w. Suprasec 2496 (Huntsman); (approx. values after 14 days of storage at room temperature)]

Pot life	minutes	according to ASTM D 2471-88	45
Hardness	Shore D	DIN EN ISO 868	65
Tensile strength	MPa	DIN EN ISO 527	16
Elongation at break	%	DIN EN ISO 527	50
Flexural strength	MPa	DIN EN ISO 178	*
Tear propagation resistance	N/mm	DIN ISO 34	*
Impact strength	KJ/m ²	DIN EN ISO 179	*
Glass transition temperature	°C	DIN EN ISO 16805	55

* in process

Form of delivery

NEUKAPOL 9028 1 kg 25 kg 200 kg 1000 kg

Storage

We recommend keeping the material in tightly closed original receptacles at temperatures of 20 - 25 °C. When duly stored, the material can be used within the shelf life indicated on the labels (the first 2 digits of the batch number indicate the week, the 3rd digit indicates the year).

Measure of precaution

With the aid of the current safety data sheets, which contain physical, ecological, toxicological and other data relating to safety, the user can inform himself on the safe handling and storage of the products.

Resin's properties

OH-functional polyol based on renewable resources (castor oil),
solvent-free, higher hardness, very hydrophobic

Reasons for development

- Universal resin
- Very good workability
- Wide range of applications
- Very good chemical resistances

Suggested field of application

- ✓ General industrial flooring
- ✓ Metal coatings
- ✓ Corrosion protection
- ✓ Tank & pipe coatings
- ✓ Adhesives

Suitable raw materials

Dispersing agent

Efka PU 4063 (BASF)
Disperbyk 2155 (BYK Chemie)

Disperbyk 2152 (BYK Chemie)
TegoDispers 652 (Tego Evonik)

Defoamer

Efka 2722 (BASF)
Tego Airex 944 (Tego Evonik)
BYK 066 (BYK Chemie)
BYK A 501 (BYK Chemie)

Efka SI 2008 (BASF)
Tego Airex 945 (Tego Evonik)
BYK A 530 (BYK Chemie)
Worlee Add 636 (Worlee Chemie)

Substrate wetting additive

Efka FL 3740 (BASF)
Tego Glide B 1484 (Tego Evonik)

BYK 333 (BYK Chemie)

Extender

Baryt Flour EWO (Sachtleben)
Feldspar FS 900 L (Quarzwerke)
Blanc Roc Micro (Minerals Girona)

Albawhite 60 (Sachtleben)
Silica Flour W 6 (Quarzwerke)

Antisettling additive

Sylsilia 350 (Sylysiamont)
Efka RM 1900 (BASF)
Tixogel MP 250 (BYK Chemie)

BYK D 410 (BYK Chemie)
Cab-O-Sil TS 720 (Cabot Corp.)
Tixogel VZ (BYK Chemie)

Water scavenger

Zeolith L-Paste (altropol)

Finmasorb PR 430 (Finma Chemie)

Formulation Proposal

FP 9028 / 2 General Industrial Floor Coating

Pos.	Raw Material	Amount	Product	Supplier
1	NEUKAPOL 9028	42.60	polyol	altropol
2	ZEOLITHE-L-PASTE	6.65	molecular sieve	altropol
3	EFKA PU 4063	1.00	dispersing agent	BASF
4	Feldspar FS 900 L	45.75	extender	Quarzwerke
5	Heucosin Special G 6517 N	3.00	pigment	Heubach
6	Tixogel MP 250	0.50	anti-settling additive	BYK Chemie
7	Tego Airex 944	0.50	defoamer	Tego Evonik
Total		100.00		

Crosslinking:

We recommend a x-linking ratio of NCO : OH of 110% or 100.00 parts of a.m. formulation require 25.87 parts of Suprasec 2496 (Huntsman).

Tinting:

We recommend to use the ALTROCOLOR PU 4500 series as pigment paste for easy tinting of the a.m. coating.

Mechanical Properties (approx. values)

			after 24h at RT	after 28 days at RT
Hardness	Shore A	DIN EN ISO 868	95	99
Hardness	Shore D	DIN EN ISO 868	54	75
Elongation at break	%	DIN EN ISO 527	58	21

Our technical service - in words, in writing or by trials - is given according to the current state of our knowledge. It does however not relieve the customer/ user from the duty to check by himself if the products supplied by us are suitable for the intended processes and purposes. Application, use and processing of the products take place beyond our control possibilities and lie therefore exclusively in the area of responsibility of the processor. Any existing property rights of third parties are to be considered. We guarantee the perfect quality of our products in accordance with our general terms and conditions of business. When handling our products you have to observe the legal rules and the rules for the industrial hygiene. As for the rest, we refer to the corresponding safety data sheets.

• 2018-01-26.4 / 12 / LW-W •