

# NEUKAPOL PN 9521

Branched Polyester/-ether

Hard elastic resin

# altropol

## Main features

- hydrophobic
- 100 % solid content
- solventfree

## Applications

- industrial floor coatings
- adhesives
- corrosion protection
- electro casting

## Product properties

			NEUKAPOL PN 9521
Colour			yellow
OH-value	mg KOH / g	DIN 53240	231 ± 15
Viscosity 25°C	mPas	Brookfield RVT	1500 ± 250
Water content	%		< 0.2
Acid number	mg KOH / g	DIN EN ISO 2114	< 3

## Properties of the mixutre [94.50 p.b.w. NEUKAPOL PN 9521 + 5 p.b.w. Zeolith Paste + 0.5 p.b.w. Defoamer NEUKAPOL PN 9079 + 57.97 p.b.w. Desmodur VL (BayerMaterialScience);

(approx. values after 14 days of storage at room temperature)]

Pot life	minutes	according to ASTM D 2471-88	45
Hardness	Shore D	DIN EN ISO 868	65
Tensile strength	MPa	DIN EN ISO 527	18
Elongation at break	%	DIN EN ISO 527	40
Flexural strength	MPa	DIN DIN EN ISO 178	*
Tear propagation resistance	N/mm	DIN ISO 34	*
Impact strength	KJ/m <sup>2</sup>	DIN EN ISO 179	*
Glass transition temperature	°C	DIN EN ISO 16805	*

\* in process

## Form of delivery

Neukapol PN 9521                      1 kg                      25 kg                      200 kg                      1000 kg

## Storage

We recommend keeping the material in tightly closed original receptacles at temperatures of 20 - 25 °C. When duly stored, the material can be used within the shelf life indicated on the labels.

## Measure of precaution

With the aid of the current safety data sheets, which contain physical, ecological, toxicological and other data relating to safety, the user can inform himself on the safe handling and storage of the products.

Our technical service - in words, in writing or by trials - is given according to the current state of our knowledge. It does however not relieve the customer/user from the duty to check by himself if the products supplied by us are suitable for the intended processes and purposes. Application, use and processing of the products take place beyond our control possibilities and lie therefore exclusively in the area of responsibility of the processor. Any existing property rights of third parties are to be considered. We guarantee the perfect quality of our products in accordance with our general terms and conditions of business. When handling our products you have to observe the legal rules and the rules for the industrial hygiene. As for the rest, we refer to the corresponding safety data sheets.

• 2018-02-05.5 / 12 / LW-W •

• [www.altropol.de](http://www.altropol.de) •

• Altropol Kunststoff GmbH • Rudolf-Diesel-Straße 9 - 13 • D-23617 Stockelsdorf • Tel. +49 451-499 60-0 •

• Fax. +49 451-499 60-20 • E - Mail: [info@altropol.de](mailto:info@altropol.de) •