

**AltroColor PAS 7000 Color Pastes** are based on a polyaspartic ester and have been developed particularly for the coloring of polyaspartics.

## Description

As our **AltroColor PAS 7000 Color Pastes Series** are based on a reactive/crosslinkable binder, a full integration into your polyaspartics is ensured.

The **AltroColor Color Pastes** thus have no or only a little influence on the Shore hardness (depending on the type of hardener/variant used) nor on the other mechanical and chemical properties.

## Chemical basis

- polyaspartic ester
- equivalent weight: 100 - 250 g/eq (depending on the pigment content and/or color shade)

## Incorporation

We recommend adding the **AltroColor Color Pastes** to the component **A** and to homogenizing thoroughly with a suitable stirrer.

## Recommended dosages (related to component A)

Normal, covering   opaque applications	5.0 %
Transparent   semi-transparent applications	0.5 to 2.5 %
Max. dosage	10.0 % (consider EEW value)

## Form of delivery

**AltroColor Color Pastes** are available as pre-formulated color shades (e.g. RAL Classic, RAL Design, NCS etc.) or as mono-pigmented pastes for mixing systems.

Further color shades, also made to customers' sample, are available on request.

## Packaging

250 g | 1 kg | 5 kg | 25 kg | 200 kg | 1000 kg

## Storage | shelf life

We recommend keeping the material cool and dry in tightly closed original receptacles at temperatures of 15 - 25 °C. When duly stored, the material can be used for 12 months. Before using the color pastes, stir up the content of the receptacle thoroughly. After use, close the receptacle again.

Description	Color Index <sup>(1)</sup>	T <sub>max</sub> <sup>(2)</sup>	Lightfastness <sup>(3)</sup>	Weather Fastness <sup>(4)</sup>	
PAS 7001	white	[IO] - PW 6	> 300 °C	8   8	5   5
PAS 7002	oxide black	[IO] - PBk 11	180 °C	8   8	5   5
PAS 7003	oxide yellow	[IO] - PY 42	180 °C	8   8	5   5
PAS 7004	oxide red	[IO] - PR 101	300 °C	8   8	5   5
PAS 7005	chrome green	[IO] - PG 17	> 300 °C	8   8	5   5
PAS 7006	ultramarine blue	[IO] - PB 29	> 300 °C	8   8	5   5
PAS 7007	black	[OR] - PBk 7	300 °C	8   8	5   4-5
PAS 7008	light-yellow	[IO] - PY 184	200 °C	8   8	5   5
PAS 7009	lemon yellow	[OR] - PY 71	160 °C	7-8   6	3   2-3
PAS 7010	yellow	[OR] - PY 83	200 °C	6-7   6	3   2-3
PAS 7011	blue PB 15:3	[OR] - PB 15:3	300 °C	8   8	5   4-5
PAS 7012	red PR 254	[OR] - PR 254	280 °C	8   8	5   4-5
PAS 7013	green	[OR] - PG 7	300 °C	8   8	5   4-5
PAS 7014	rose	[OR] - PR 122	300 °C	7-8   8	4   4-5
PAS 7015	violet	[OR] - PV 23	280 °C	8   7-8	4-5   4
PAS 7016	red	[OR] - PR 48:2	180 °C	7   5	3   2-3
PAS 7017	cobalt blue	[IO] - PB 36	300 °C	8   8	5   5
PAS 7018	cobalt green	[IO] - PG 50	300 °C	8   8	5   5

(1) [IO] inorganic; [OR] organic

(2) All indicated values relating to thermal stability, light fastness and weather fastness were adopted from the pigment producer and are to be regarded as references only. We strongly recommend carrying out tests on your own!

(3) Lightfastness [full tone | brightening]: evaluation as per 8-stage blue scale: 1 - very bad | 8 - excellent

(4) Weather fastness [full tone | brightening]: evaluation as per 5-stage grey scale: 1 - very bad | 5 - excellent

## Measure of precaution

With the aid of the current safety data sheets, which contain physical, ecological, toxicological and other data relating to safety, the user can inform himself on the safe handling and storage of the products.

Our technical service - in words, in writing or by trials - is given according to the current state of our knowledge. It does however not relieve the customer / user from the duty to check by himself if the products supplied by us are suitable for the intended processes and purposes. Application, use and processing of the products take place beyond our control possibilities and lie therefore exclusively in the area of responsibility of the processor. Any existing property rights of third parties are to be considered. We guarantee the perfect quality of our products in accordance with our general terms and conditions of business. When handling our products you have to observe the legal rules and the rules for the industrial hygiene. As for the rest, we refer to the corresponding safety data sheets.

• 2020-11-18.6 / 12 / LW-W •

• [www.altropol.de](http://www.altropol.de) •

• Altropol Kunststoff GmbH • Rudolf-Diesel-Straße 9 - 13 • D-23617 Stockelsdorf • Tel. +49 (0)451-499 60-0 •

• Fax. +49 (0)451-499 60-20 • E - Mail: [info@altropol.de](mailto:info@altropol.de) •